

DONNEES PHONIQUES

	COMPOSITION	Rw (C, Ctr) dB	Rw + C [dB] dB Rose	Rw + Ctr [dB] dB Route	Epaisseur (mm)
Doubles vitrages	4/16/4	32 (-2,-5)	30	27	24
	4/18/6	36 (-1,-5)	35	31	28
	6/16/4	36 (-2,-6)	34	30	26
	6/16/6	34 (-1,-5)	33	31	28
	8/12/6	37 (-1,-5)	36	32	26
	8/16/5	38 (-2,-5)	36	33	29
	10/12/6	39 (-1,-5)	38	34	28
	10/12/8	38 (-2,-4)	36	34	30
	10/14/6	39 (-1,-5)	38	34	30
	33.2/10/33.2	34(-1,-5)	33	29	24
Doubles vitrages avec feuilleté ordinaire	33.2/16/4	37 (-2,-6)	35	31	27
	44.2/10/6	39 (-2,-5)	37	34	25
	44.2/12/4	36 (-2,-6)	34	30	25
	44.2/12/44.2	38 (-1,-5)	37	33	30
	44.2/14/6	40 (-2,-6)	38	34	29
	44.2/16/4	38 (-2,-6)	36	32	29
	44.2/16/6	41 (-2,-5)	39	36	31
	44.2/16/33.2	41 (-3,-7)	38	34	32
	44.2/20/8	39 (-2,-6)	37	33	37
	44.2/20/10	42 (-2,-5)	40	37	39
	44.2/24/6	42 (-2,-6)	40	36	39
	55.2/16/8	41 (-2,-5)	39	36	35
	66.2/20/10	43 (-1,-4)	42	39	43
Doubles vitrages avec feuilleté acoustique	33.2 acoustique/16/4	37 (-2,-6)	35	31	27
	33.2 acoustique/16/44.2	41 (-3,-7)	38	34	30
	44.2 acoustique/12/6	41 (-3,-7)	38	34	27
	44.2 acoustique/16/6	42 (-2,-6)	40	36	31
	44.2 acoustique/20/6	43 (-3,-7)	40	36	35
	44.2 acoustique/12/8	41 (-3,-7)	38	34	29
	44.2 acoustique/16/8	42 (-2,-6)	40	34	33
	44.2 acoustique/20/8	44 (-3,-7)	41	37	37
	44.2 acoustique/12/10	44 (-2,-6)	42	38	31
	44.2 acoustique/16/10	45 (-2,-6)	43	39	35
	44.2 acoustique/20/10	46 (-1,-5)	45	41	39
	44.6 acoustique/16/6	43 (-2,-7)	41	36	33
	44.6 acoustique/16/10	46 (-1,-5)	45	41	37
	64.2 acoustique/16/4	40 (-2,-6)	38	34	31
	64.2 acoustique/16/6	42 (-2,-6)	40	36	33
	64.2 acoustique/16/44.2	44 (-2,-6)	42	38	36
	64.2 acoustique/16/44.2 acoustique	46 (-2,-7)	44	39	36
	66.2 acoustique/10/8	42 (-1,-5)	41	37	31
	66.2 acoustique/12/10	44 (-1,-4)	43	40	35
	66.2 acoustique/16/10	45 (-1,-4)	44	41	39
	66.2 acoustique/12/44.2 acoustique	46 (-2,-6)	44	40	34
	66.2 acoustique/16/44.2 acoustique	47 (-1,-6)	46	41	38
	66.2 acoustique/20/44.2 acoustique	48 (-2,-6)	46	42	42
	88.2 acoustique/16/44.2 acoustique	49 (-1,-5)	48	44	42
Triple vitrages	4/10/4/10/4	32 (-1,-5)	31	27	32
	4/12/4/12/4	32 (-1,-5)	31	27	36
	4/14/4/14/4	32 (-1,-5)	31	27	40
	4/16/4/16/4	33 (-2,-5)	31	28	44
	6/14/4/14/6	36 (-2,-5)	34	31	44
Triples vitrages avec feuilleté ordinaire	44.2/10/4/10/4	38 (-2,-6)	36	32	37
	44.2/10/4/10/44.2	42 (-2,-6)	40	34	42
	44.2/12/4/12/4	39 (-2,-6)	37	33	41
	44.2/12/4/12/6	40 (-1,-5)	39	35	43
Triples vitrages avec feuilleté acoustique	33.2 acoustique/14/4/14/8	44 (-2,-6)	42	38	47
	44.2 acoustique/14/4/14/4	41 (-2,-5)	39	36	45
	44.2 acoustique/14/6/14/10	48 (-2,-7)	46	41	
	44.2 acoustique/14/4/14/33.2 acoustique	44 (-2,-6)	42	38	48
	64.2 acoustique/14/6/14/44.2 acoustique	48 (-2,-7)	46	39	54

dB (Rw) : indice d'affaiblissement acoustique selon normes ISO 140-3 : 2004 et ISO 717-1 : 2006
Les compositions du tableau ci-dessus bénéficient d'un certificat.